PRODUCT DATA SHEET

ESGAL 6001

ESGAL 6001 is an air-drying solvent based Long Oil Alkyd Resin based on Soya oil having good color fastness, body, durability and high gloss potential. It is known for its green attributes like biobased raw materials and optimal recycle contents.

This Resin is diluted in MTO and recommended for use in solvent-based paints, lacquers and related products for air-drying applications. It offers excellent hydrocarbon solvent tolerance and very good pigment & extender binding capability.

Product Data:

- Appearance : Transparent Viscous Liquid
- Oil Length : 60 ± 2
- Solid Content : 60 ± 2 (120°C, 1h)
- Specific Gravity : 0.94 ± 0.2 (30°C)
- Acid Value : Max. 14 (mg KOH/g)
- Viscosity (50% in MTO) : 200 – 260 Sec (B4 Cup/30°C)

Performance Highlights :

Provides:

- Excellent Gloss & Gloss Retention
- Very good Drying and Hardness
- Excellent Flow & Levelling

PRODUCT DATA SHEET

ESGAL 6001

Drying Time:

With 0.6% Stroncium (12%), 0.2% Cobalt (12%), 0.5% Manganese (10%) & 0.6g Calcium (6%) in Alkyd Resin (50% diluted with MTO), drying time @30°C on glass plate (Sheen Film Applicator, 78 micron) has been found :

- Surface Dry ≤1 hr
- Tack-Free Dry 5 -7 hrs
- Hard Dry Overnight

*Drying time is related to relative humidity

Storage & Stability:

Highly recommended to store indoors in the original, unopened and undamaged containers in a dry place at storage temperatures between 5 & 30°C. Exposure to direct sun shine should be avoided.Under the above-mentioned storage conditions, stability of the resin will be 9-12 months ex-work.

Contact

For feedback or further information, please feel free to contact us at info@tulonmaterials.com.

Tulon Materials Pvt Ltd

Address: A212, 2nd Floor, Plot No 11 and 11A, Punit Industrial Premises Industrial Area TTC, MIDC, Turbhe, Navi Mumbai – 400705

Website: www.tulonmaterials.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Tulon Materials Pvt Ltd expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. Theinformation provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations. ESGAL® is a registered trademark of Tulon Materials Pvt Ltd

2025 Tulon Materials Pvt Ltd All rights reserved.